



Caratteristiche tecniche Technical characteristics Caractéristiques techniques Technische merkmale		Norma di riferimento Reference standard Norme de reference Prüfmethode			Valore richiesto Required value Valeur requise Sollwert	
	Dimensioni Dimensions Dimensions Abmessungen	ISO 10545-2			Conforme Compliant Conforme Konform	
	Assorbimento d'acqua Water absorption Absorption d'eau WASSERAUFNAHME	ISO 10545-3			≤ 0,5 %	
	Resistenza a flessione Modulus of rupture Resistance a la flexion Biegefestigkeit	ISO 10545-4			Modulus of ropture R ≥35 N/mm ² Breaking strength S ≥1300 n	
	Resistenza all'abrasione Abrasion resistance Résistance à l'abrasion Abriebbeständigkeit	ISO 10545-7			PEI Solo per piastrelle smaltate Only for glazed tiles	
	Dilatazione termica lineare Linear thermal expansion Dilatation thermique lineaire Lineare Wärmeausdehnung	ISO 10545-8			≤ 9x10 ⁻⁵ °C ⁻¹	
	Resistenza agli sbalzi termici Thermal shock resistance Resistance aux ecarts de tempe- rature ITemperaturwechselbeständigkeit	ISO 10545-9			Resistente Resistant Resistant Beständig	
	Resistenza al gelo Frost resistance Resistance au gel Frostbeständigkeit	ISO 10545-12			Resistente Resistant Resistant Beständig	
	Resistenza agli acidi ed alle basi Acid and alkali resistance Resistance aux acides et aux bases Säure- und Laugenbeständigkeit	ISO 10545-13			CLASS GB MIN.	
	Resistenza all'attacco chimico Chemical resistance Resistance à l'attaque chemique Chemische Beständigkeit	ISO 10545-13			CLASS GB MIN.	
	Resistenza alle macchie Stain resistance Resistance au taches Fleckenbeständigkeit	ISO 10545-14			CLASS 3 MIN.	
	Coefficiente di attrito (scivolosità) Friction coefficient (slipperiness) Coefficient de friction (glissement) Reibungskoeffizient (Rutschigkeit)	BCR - Italia DM del 14-06-89			ASTM - USA ASTM C1028	
		Dry rubber 0,62	Wet rubber 0,51	Dry leather 0,62	Dry neolythe 0,69	Wet neolythe 0,62

THE PRODUCTS HAVING AN ABSORPTION < 0,5% ARE CLASSIFIED ACCORDING THE UNI CEN STANDARDS “FULLY VITRIFIED TILES” AND ACCORDING TO THE ASTM STANDARDS “IMPERVIOUS TILES”